

amendments to be made via the substitute specification relative to the specification as it stood immediately prior to this amendment.

**IN THE DRAWINGS:**

New copies of Figures 1 to 4 are included in triplicate as color photographs permanently mounted on bristol board. A petition to accept color photographs and the \$130.00 petition fee are also included, on a separate paper, as are black-and-white photocopies of the color photographs.

New copies of Figures 5 to 36 have been provided with a different identification key which clearly associates each profile with the proper element. The marker symbols in the key have been circled in red, as has a representative marker symbol on each line of each figure. The Examiner's approval of these drawings is requested.

**REMARKS**

Applicants' undersigned counsel thanks the Examiner for the very careful and thorough examination given the application. In this response applicant has provided a substitute specification as required in the previous Office action. Corrected drawings have been provided for Figs. 1-36, along with the required petition and fee. In addition, claim 73 has been amended to comply with 35 U.S.C. § 112, second paragraph.

In the Office action, the Examiner rejected claim 73 under 35 U.S.C. § 112, second paragraph, as being indefinite for failing to particularly point out and distinctly claim the subject matter which applicant regards as the invention. Specifically, the Examiner found the term "phosphoric ions" to be vague and indefinite. The use of the term "phosphoric" was a product of translation of the German term "phosphorhaltig". Applicant has included a copy of a page from a German/English chemistry dictionary showing this definition. As shown in a photocopy from another German/English chemistry dictionary,

the term "phosphorhaltig" is equivalent to the English "containing phosphorus". Claim 73 has been amended accordingly. The Markush grouping now includes, inter alia, "phosphorus-containing ions". As amended, claim 73 complies with the requirements of 35 U.S.C. § 112, second paragraph.

As mentioned above, the substitute specification has been amended to correct numerous matters objected to by the Examiner in the previous Office action. The substitute specification contains no new matter. A summary of the amendments follows:

The notation "(Fig. 2)" has been removed from the abstract.

All references to claim numbers have been removed.

A brief description of Figure 38 has been added to the specification.

The reference to Figure 1 as containing values of the rate constant  $k_j$  has been changed to refer to Figure 38.

The references to page numbers of the specification have been replaced by identification of the conventional chromatations by referring to the specific method groups presented in DIN 50960.

The kinetics terms have been edited for greater viewing clarity.

Section headings have been added to subdivide the text into specific portions having recognizable subject matter.

The specification has been amended to provide proper antecedent basis for the claimed subject matter as set forth in claims 58 to 119 including claim 73 as amended. No new matter has been added.

References to "lanthanides" in the specification have been replaced with the symbols for the actual chemical elements that are commonly referred to as the "lanthanides".

In addition, former page 6 line 36 (now page 8 line 19 in the substitute specification) has been amended by deleting "in %" as was done in the Second Preliminary Amendment.

New copies of Figures 1 to 4 are included in triplicate as color photographs permanently mounted on bristol board. In the original PCT filing, these photographs were presented in color. Black-and-white photocopies were then transmitted to the USPTO by the International Bureau in connection with entry into the U. S. national phase. These color photographs are now filed to satisfy the requirements of 37 CFR 1.84. A petition to accept color photographs and appropriate fee are also included. Also, the text which originally appeared in Figs. 1-4 has been moved to the "Brief Description of the Drawings", along with translations of certain German terms.

As required by 37 CFR 1.84, the substitute specification includes the form paragraph required at the beginning of the "Brief Description of the Drawings" section, indicating that at least one color photograph was filed in the case.

New copies of Figures 5 to 36 have been provided with a different identification key which clearly associates each profile with the proper element. Like the color photographs from Figs. 1-4, the graphs were originally presented in color, with colored lines and a color key. Transmission by black-and-white photocopy made it impossible to identify and distinguish the lines. Rather than petition the Office to accept color graphs, however, applicant has supplied a different key to the graph. The lines on the graphs are now identified either by marker symbols appearing on each line or by a different line style. Each line on each graph has one representative marker symbol circled in red. In addition to these indications, all marker symbols in the key for each graph have been circled in red. The remaining marker symbols on the lines in the graphs were not marked in red due to their large number and close proximity; confusion rather than clarity would result if each marker symbol were marked. If the Examiner would nonetheless like each marker symbol marked, please notify the undersigned promptly.

As all objections and rejections from the Office action have now been addressed, applicant respectfully submits that the application is in condition for allowance. A notice of

allowance is therefore respectfully requested. If there are any fees required by this communication not covered by an enclosed check or checks, please charge such fees to our Deposit Account No. 16-0820, order No. 31716.

Respectfully submitted,  
PEARNE & GORDON LLP

By John P. Murtaugh  
John Murtaugh, Reg. No. 34226

526 Superior Avenue East, Suite 1200  
Cleveland, Ohio 44114-1484  
(216) 579-1700

Date: Jan. 31, 2001

Description

5 Chromium(VI)-Free Conversion Layer and Method for Producing It

FIELD OF THE INVENTION

The present invention relates to chromium(VI)-free, chromium(III)-  
containing, substantially coherent conversion layers [according to claim  
10 1], a method for producing them [according to claim 7], a concentrate  
[according to claim 10], a passivation bath [according to claim 14], a  
passivating method [according to claim 20], a passive layer [according to  
claim 24], and a conversion layer [according to claim 28].

15 BACKGROUND OF THE INVENTION

Metallic materials, in particular iron and steel, are plated with zinc or  
cadmium in order to protect them from corrosive environmental  
influences. The corrosion protection of zinc resides in the fact that it is  
20 even less precious than the base metal and therefore at first exclusively  
draws the corrosive attack; it acts as a sacrificial layer. The base metal  
of the respective zinc-plated component remains unimpaired as long as it  
is continuously covered with zinc, and the mechanical functionality  
remains preserved over longer periods of time than in the case of parts  
25 not plated with zinc. Thicker zinc layers naturally afford higher corrosion  
protection than thin layers inasmuch as corrosive erosion of thicker  
layers simply takes more time.

The corrosive attack on the zinc layer, in turn, can be greatly delayed by  
30 application of a chromation, or chromate coating, whereby corrosion of  
the base metal is even further postponed than by mere zinc plating. A  
considerably better corrosion protection is afforded by the zinc/chromate  
layer system is than by a mere zinc layer of identical thickness. Moreover  
by means of chromation the optical deterioration of a component due to

environmental influences is further postponed - the corrosion products of zinc, referred to as "white rust", equally interfere with the optical appearance of a component.

- 5 The advantages of an applied chromation are so important that almost any galvanically zinc-plated surface is in addition chromate coated as well. The prior art knows four chromations named after their colorations, which are each applied by treating (immersion, spraying, rolling) a zinc-plated surface with the corresponding aqueous chromate coating solution.
- 10 Moreover yellow and green chromations for aluminum are known which are produced analogously. In any case, these are variously thick layers of substantially amorphous zinc/chromium oxide (or aluminum/chromium oxide) with non-stoichiometric compositions, a certain water content, and inserted foreign ions. These are known and classified into method groups
- 15 in accordance with German Industrial Standard (DIN) 50960, Part 1:

#### **1) Colorless and blue chromations, Groups A and B**

- The blue chromate layer has a thickness of up to 80 nm, is weakly blue in
- 20 its inherent color and presents a golden, reddish, bluish, greenish or yellow iridescent coloring brought about by refraction of light in accordance with layer thicknesses. Very thin chromate layers lacking almost any inherent color are referred to as colorless chromations (Group A). The chromate coating solution may in either case consist of
- 25 hexavalent as well as trivalent chromates and mixtures of both, moreover conducting salts and mineral acids. There are fluoride-containing and fluoride-free variants. Application of the chromate coating solutions is performed at room temperature. The corrosion protection of unmarred blue chromations amounts to 10-40 h in the salt spray cabinet according
- 30 to DIN 50021 SS until the first appearance of corrosion products. The minimum requirement for Method Groups A and B according to DIN 50961 Chapter 10 Table 3 is 8 h for drumware and 16 h for shelfware.

## **2) Yellow chromations, Group C**

The yellow chromate layer has a thickness of approx. 0.25-1  $\mu\text{m}$ , a golden yellow coloring, and frequently a strongly red-green iridescent coloring. The chromate coating solution substantially consists of hexavalent chromate, conducting salts and mineral acids dissolved in water. The yellow coloring is caused by the significant proportion (80-220  $\text{mg}/\text{m}^2$ ) of hexavalent chromium which is inserted besides the trivalent chromium produced by reduction in the course of the layer formation reaction. Application of the chromate coating solutions is performed at room temperature. The corrosion protection of unmarred yellow chromations amounts to 100-200 h in the salt spray cabinet according to DIN 50021 SS until the first appearance of corrosion products. The minimum requirement for Method Group C according to DIN 50961 Chapter 10 Table 3 amounts to 72 h for drumware and 96 h for shelfware.

## **3) Olive chromations, Group D**

The typical olive chromate layer has a thickness of up to 1.5  $\mu\text{m}$  and is opaquely olive green to olive brown. The chromate coating solution substantially consists of hexavalent chromate, conducting salts and mineral acids dissolved in water, in particular phosphates or phosphoric acid, and may also contain formates. Into the layer considerable amounts of chromium(VI) (300-400  $\text{mg}/\text{m}^2$ ) are inserted. Application of the chromate coating solutions is performed at room temperature. The corrosion protection of unmarred olive chromations amounts to 200-400 h in the salt spray cabinet according to DIN 50021 SS until the first appearance of corrosion products. The minimum requirement for Method Group D according to DIN 50961 Chapter 10 Table 3 is 72 h for drumware and 120 h for shelfware.

#### **4) Black chromations, Group F**

The black chromate layer is fundamentally a yellow or olive chromation having colloidal silver inserted as a pigment. The chromate coating

5 solutions have about the same composition as yellow or olive chromations and additionally contain silver ions. With a suitable composition of the chromate coating solution on zinc alloy layers such as Zn/Fe, Zn/Ni or Zn/Co, iron, nickel or cobalt oxide will be incorporated into the chromate layer as a black pigment so that silver is not required  
10 in these cases. Into the chromate layers considerable amounts of chromium(VI) are inserted, namely between 80 and 400 mg/m<sup>2</sup> depending on whether the basis is a yellow or olive chromation.

Application of the chromate coating solutions is performed at room temperature. The corrosion protection of unmarred black chromations on  
15 zinc amounts to 50-150 h in the salt spray cabinet according to DIN 50021 SS until the first appearance of corrosion products. The minimum requirement for Method Group E according to DIN 50961 Chapter 10 Table 3 is 24 h for drumware and 48 h for shelfware. Black chromations on zinc alloys are considerably above the specified values.

20

#### **5) Green chromations for Aluminum, Group E**

The green chromation on aluminum (known under the name of aluminum green) is of a matt green and not iridescent. The chromate coating

25 solution substantially consists of hexavalent chromate, conducting salts and mineral acids dissolved in water as well as particularly phosphates and silicofluorides. Contrary to a prevailing opinion the formed chromate/phosphate layer is, as evidenced by iodised starch tests, not always 100% chromium(VI)-free. The production of aluminum green in  
30 chromate coating solutions exclusively on the basis of chromium(III) is not known.

In accordance with the prior art, thick chromate layers affording high corrosion protection > 100 h in the salt spray cabinet according to DIN



50021 SS or ASTM B 117-73 until the appearance of first corrosion products according to DIN 50961 (June 1987) Chapter 10, in particular Chapter 10.2.1.2, in the absence of sealing or any other particular aftertreatment (DIN 50961, Chapter 9) may only be produced by

5 treatment with dissolved, markedly toxic chromium(VI) compounds. Accordingly the chromate layers having the named requirements to corrosion protection still retain these markedly toxic and carcinogenic chromium(VI) compounds, which are, moreover, not entirely immobilised in the layer. Chromate coating with chromium(VI) compounds is

10 problematic with respect to workplace safety. Use of zinc-plated chromations produced with chromium(VI) compounds, such as the widespread yellow chromations e.g. on screws, constitutes a potential hazard to the population and increases the general cancer risk.

15 US 43 84 902, in particular with Examples 1, 2, 4 and 5, describes conversion layers which satisfy the requirements in the salt spray test. In all of the cases, these are cerium-containing layers presenting a **yellowish** coloration which is accentuated by the cerium(IV) ion. The examples only contain cerium(III), and hydrogen peroxide as an oxidant, in the bath

20 solution. In the description it is set forth that hydrogen peroxide in the acidic medium does not represent an oxidant for Ce(III), however during deposition the pH value nevertheless rises so high at the surface that a sufficient amount of Ce(IV) may be generated. The yellowish coloration achieved by this bath composition indeed appears to indicate that an

25 oxidation has taken place - however, only an oxidation from Ce(III) to Ce(IV). Tetravalent cerium is an even more powerful oxidant than hexavalent chromium, for which reason Ce(IV) will produce from Cr(III) the Cr(VI) which is to be avoided. Cr(VI) has a very strong yellow coloration and is known as an anticorrosion agent. The layer described in

30 US 43 84 902 is thus not free of hexavalent chromium.

## BRIEF DESCRIPTION OF THE DRAWINGS

The file of this patent contains at least one drawing executed in color. Copies of this patent with color drawings will be provided by the Patent Office upon request and payment of the necessary fee.

5

Fig. 1 is a color comparison of various passive layers; it shows a comparison of the present invention with blue and yellow chromations. The substrate is zinc-plated screws. The left picture half is blue chromation; the center is the invention; the right picture half is yellow  
10 chromation.

Fig. 2 is a scanning electron microscope image (40,000 ×) showing a comparison of the present invention ("chromitation") with blue and yellow chromations. "Gelbchromatierung" means yellow chromation;  
15 "Chromitierung" means chromitation; "Blauchromatierung" means blue chromation; "Zink" means zinc.

Fig. 3 is a color photo showing the band width of the iridescent coloring in accordance with the present invention on zinc surfaces (zinc-plated  
20 screws);

Fig.4, a comparison test with EP O 034 040, shows coatings of the prior art in accordance with EP O 034 040. Example 16 is on the left hand side, Example 17 is on the right hand side. The upper picture half, on  
25 the outer left and right, shows a black cloth whereby the abrasions on the metal sheets shown in the top picture half were obtained. Layer portions -- discernible as whitish stains -- are on both pieces of cloth. The lower picture half shows the unmarred layers of the prior art. The substrate is zinc-plated steel sheet.

30

Figs. 5 to 36 show depth profile analyses of layers according to the invention and layers resulting from the conventional blue and yellow chromations, wherein the depth profile analyses were measured by glow-discharge spectrometry (spectrometer: JY5000RF);

Fig. 37 is a table containing the evaluation of the depth profile analyses of Figs. 5 to 36.

5 Fig. 38 is a computer simulation of the kinetic model of chromate coating of zinc for various rate constants.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS OF THE INVENTION

- 10 The layer according to the invention is, however, produced in the absence of any oxidant and consequently free of hexavalent chromium. This can in particular be seen from the fact that the layer according to the invention is not yellow.
- 15 Even where the yellow coloration and the enhanced corrosion protection should be brought about by nothing but Ce(IV), the layer according to the invention affords the desired corrosion protection even without this very costly and rare addition.
- 20 US 43 59 348 also describes conversion layers which satisfy the above mentioned requirements in the salt spray test. These, too, in all cases are cerium-containing layers which present the yellowish coloration accentuated by the cerium(IV) ion. This document thus does not exceed US 43 84 902.

25

It is therefore an object of the present invention to furnish a chromium(VI)-free, thick conversion layer having a high chromium content on zinc or zinc alloys.

- 30 [With respect to a layer this object is attained by the features of claims 1, 24 and 28, with respect to method technology by the features of claims 7 and 20, and with respect to a composition for carrying out the method of the invention by the features of claims 10 and 14.]

For the purposes of the present inventions the applicant coined the term "chromitation" in order to clearly distinguish the present invention from the chromations which are customary in the prior art, and in order to make clear that neither the obtained conversion layer nor the

5 compositions (concentrates/passivation baths) whereby the coatings according to the invention are produced contain the toxic chromium(VI), whereas the obtained corrosion protection nevertheless is superior to that of yellow chromation.

10 EP 00 34 040 A1 does describe a multiplicity of layers, of the larger group of which (produced under the standard conditions set forth by Barnes/Ward) the color is not specified, however referred to as clear. Two Examples, namely Nos. 16 and 17, describe a greenish borate-containing layer described as cloudy-dull to non-transparent.

15

Example 14 describes a layer affording a corrosion protection of only 4 hours.

[The subclaims represent preferred embodiments of the present  
20 invention.]

Concerning the features of [claim 2] the invention, the following should be noted:

25 In glow-discharge spectrometry several elements could not be detected while others could not be calibrated. Therefore the chromium/(chromium + zinc) phases were compared to each other. The chromium index is the average chromium content [in %] in the layer > 1% Cr<sub>2</sub> multiplied by the layer thickness. The chromium index is  
30 proportional to the chromium quantity on the surface (mg/m<sup>2</sup>).

Further advantages and features of the present invention result from the description of embodiments and from theoretical reflections which are not binding on the one hand and were, on the other hand, carried out by

the inventors while having knowledge of the present invention, and by referring to the drawings, [, wherein:

Fig. 1 shows a comparison of the present invention with blue and yellow  
5 chromations;

Fig. 2 is a scanning electron microscope image (40,000 ×) showing a comparison of the present invention ("chromitation") with blue and yellow chromations;

10

Fig. 3 is a color photo showing the band width of the iridescent coloring in accordance with the present invention on zinc surfaces;

15

Fig.4 shows coatings of the prior art in accordance with EP 0 034 040;

Figs. 5 to 36 show depth profile analyses of layers according to the invention and layers resulting from the conventional blue and yellow chromations, wherein the depth profile analyses were measured by glow-discharge spectrometry (spectrometer: JY5000RF); and

20

Fig. 37 is a table containing the evaluation of the depth profile analyses of Figs. 5 to 36.]

The conversion layer preferably has a layer thickness of about 100 to  
25 1000 nm, the conversion layer having across the conversion layer  
thickness a chromium content of greater than 1% based upon zinc and  
chromium, the conversion layer having an average chromium content of  
more than approximately 5% based on zinc and chromium, and the  
conversion layer having a chromium index greater than approximately  
30 10, wherein the chromium index is defined as the average chromium  
content (chromium/(chromium + zinc)) in the layer greater than 1% Cr,  
multiplied by the layer thickness in nm.

Preferably the conversion layer has a chromium-rich zone greater than

approximately 20% chromium, based upon zinc and chromium in the conversion layer, of more than approximately 15 nm.

The conversion layer may be transparent, clear, or substantially colorless. The conversion layer may be iridescent, and may present multi-colored iridescence.

For enhanced corrosion protection the conversion layer may additionally contain one or more components selected from the group consisting of silicate, cerium, aluminum, and borate. The conversion layer may contain cobalt or one or more metal compounds having valences of 1 to 6. The conversion layer may include one or more metal compounds selected from the group consisting of Na, Ag, Al, Co, Ni, Fe, Ga, In, La, Ce, Pr, Nd, Pm, Sm, Eu, Gd, Tb, Dy, Ho, Er, Tm, Yb, Lu, Zr, Sc, Ti, V, Cr, Mn, Cu, Zn, Y, Nb, Mo, Hf, Ta, and W.

The conversion layer may include one or more ions selected from the group consisting of anions and may include one or more ions selected from the group consisting of halide ions, sulfurous ions, nitrate ions, phosphorus-containing ions, carboxylic acid anions, and silicon-containing anions.

The conversion layer may include one or more ions selected from the group consisting of chloride ions, sulfate ions, phosphate ions, diphosphate ions, linear and cyclic oligophosphate ions, linear and cyclic polyphosphate ions, hydrogen phosphate ions, and silicate anions.

The conversion layer may include one or more materials selected from the group consisting of polymers, corrosion inhibitors, silicic acids, surfactants, polyols, organic acids, amines, plastics dispersions, dyes, pigments, chromogenic agents, amino acids, siccatives, and dispersing agents.

The conversion layer may include one or more materials selected from

the group consisting of organic polymers, colloidal or disperse silicic acids, diols, triols, monocarboxylic acids, carbon black, metal chromogenic agents, glycin, and cobalt siccatives.

- 5 The conversion layer may include one or more materials selected from the group consisting of dyes and color pigments.

In a method according to the invention, a metallic surface preferably is treated with a solution of at least one chromium (III) complex and at least  
10 one salt, wherein chromium (III) is present in the solution in a concentration of approximately 5 to 100 g/l; and the chromium (III) complex has ligand replacement kinetics more rapid than the fluoride replacement kinetics in chromium (III)-fluorocomplexes. This method produces a chromium (VI)-free conversion layer affording at least the  
15 corrosion protection of conventional chromium (VI)-containing yellow chromations.

Metallic surfaces suitable for application of the conversion layer include zinc, zinc alloy, and zinc alloy with iron.

20

In the method the treating is preferably carried out at an elevated temperature, or at a temperature of 20-100°C, more preferably 20-80°C, more preferably 30-60°C, more preferably 40-60°C.

- 25 In the method the chromium (III) complex preferably has chelate ligands which are selected from the group consisting of dicarboxylic acids, tricarboxylic acids, hydroxycarboxylic acids, acetylacetone, urea, urea derivatives, mixtures thereof, among each other as well as in mixed complexes with inorganic anions and H<sub>2</sub>O.

30

In the method the chromium (III) complex preferably has chelate ligands which are selected from the group consisting of oxalic, malonic, succinic, glutaric, adipic, pimelic, suberic, azelaic and sebacic acids, mixtures thereof, and in mixed complexes with inorganic anions and H<sub>2</sub>O.

In the method the chromium (III) complex preferably has chelate ligands which are selected from the group consisting of maleic acid, phthalic acid, terephthalic acid, tartaric acid, citric acid, malic acid, ascorbic acid, mixtures thereof, and in mixed complexes with inorganic anions and  
5 H<sub>2</sub>O.

In the method the chromium (III) complex preferably has chelate ligands which are selected from the group consisting of malonic acid and malonic acid in mixed complexes with inorganic anions and H<sub>2</sub>O.  
10

The method may be performed repeatedly on the metallic surface.

In the method the treating may be carried out at a temperature of 20 to 100°C with rinsing water recycling over at least 2 cascaded rinsing  
15 stages; a blue chromation may be performed in one of the rinsing stages.

The method may include an immersion period of between approximately 15 and 200 seconds or of between approx. 15 and 100 seconds or an immersion period of approx. 30 seconds.  
20

A passivation bath for passivating a metal surface preferably comprises chromium (III) in a concentration of approximately 5 to 100 g/l; the chromium (III) being present in the bath in the form of at least one chromium (III) complex having ligand replacement kinetics more rapid  
25 than the fluoride replacement kinetics in chromium (III)-fluorocomplexes.  
The bath preferably substantially contains chromium (III) as a passivating component.

The chromium (III) complex in the bath preferably is selected from  
30 complexes with chromium (III) and at least one chelate ligand selected from the group consisting of dicarboxylic acids, tricarboxylic acids, hydroxycarboxylic acids, acetylacetone, urea, urea derivatives, mixtures thereof, among each other as well as in mixed complexes with inorganic anions and H<sub>2</sub>O.



The chromium (III) complex in the bath may be selected from complexes with chromium(III) and at least one chelate ligand selected from the group consisting of oxalic, malonic, succinic, glutaric, adipic, pimelic, suberic, azelaic and sebacic acids, mixtures thereof, and in mixed complexes with  
5 inorganic anions and H<sub>2</sub>O.

The chromium (III) complex in the bath may be selected from complexes with chromium(III) and at least one chelate ligand selected from the group consisting of maleic acid, phthalic acid, terephthalic acid, tartaric acid,  
10 citric acid, malic acid, ascorbic acid, mixtures thereof, and in mixed complexes with inorganic anions and H<sub>2</sub>O.

The chromium (III) complex in the bath may be selected from complexes with chromium(III) and at least one chelate ligand selected from the group  
15 consisting of malonic acid and malonic acid in mixed complexes with inorganic anions and H<sub>2</sub>O.

The bath may also include one or more components selected from the group consisting of sealers, dewatering fluids, additional metal  
20 compounds, anions, polymers, corrosion inhibitors, silicic acids, surfactants, polyols, organic acids, amines, plastics dispersions, dyes, pigments, chromogenic agents, amino acids, siccatives and dispersing agents. The bath may also include one or more components selected from the group consisting of 1- to 6-valent metal compounds, halide ions,  
25 sulfurous ions, nitrate ions, phosphoric ions, carboxylic acid anions, silicon-containing anions, organic polymers, colloidal or disperse silicic acids, diols, triols, monocarboxylic acids, carbon black, metallic chromogenic agents, glycin, and cobalt siccatives. The bath may also include one or more components selected from the group consisting of  
30 metal compounds of Na, Ag, Al, Co, Ni, Fe, Ga, In, La, Ce, Pr, Nd, Pm, Sm, Eu, Gd, Tb, Dy, Ho, Er, Tm, Yb, Lu, Zr, Sc, Ti, V, Mn, Cu, Zn, Y, Nb, Mo, Hf, Ta, and W, chloride ions, sulfate ions, phosphate ions, diphosphate ions, linear and cyclic oligophosphate ions, linear and cyclic polyphosphate ions, hydrogen phosphate ions and silicate anions.

- Chromium (III) is preferably present in the bath in a concentration of approximately 5 g/l to 80 g/l, more preferably approximately 5 g/l to 60 g/l, more preferably approximately 10 g/l to 30 g/l, more preferably approximately 20 g/l. The bath preferably has a pH between
- 5 approximately 1.5 and 3, more preferably approximately 2 to 2.5. The temperature of the bath is preferably approx. 20 to 100°C, more preferably approximately 20 to 80°C, more preferably approximately 30 to 60 °C, more preferably approx. 40 to 60°C.
- 10 To facilitate preparation of a passivation solution, a concentrate may be prepared. The concentrate preferably substantially contains chromium (III) for a passivating component, wherein the chromium (III) is present in the form of at least one complex having ligand replacement kinetics more rapid than the fluoride replacement kinetics in chromium (III)-
- 15 fluorocomplexes. The concentrate is preferably in either liquid or solid form. The concentrate may be used for producing a passivation solution for passivating a metal surface such as a metal surface selected from the group consisting of zinc, cadmium, aluminum and alloys of these metals among each other and/or with iron or other metals.

20

### Example 1

The following experiment was carried out:

- 25 Small steel parts were bright-zinc coated electrolytically (approx. 15 m) and, following galvanisation, singly immersed in a boiling (approx. 100°C), aqueous solution containing:

- 100 g/l  $\text{CrCl}_3 \cdot 6 \text{H}_2\text{O}$  (trivalent chromium salt)  
100 g/l  $\text{NaNO}_3$   
30 15.75 g/l  $\text{NaF}$   
26.5 g/l citric acid • 1 aq

which had previously been adjusted to a pH value of 2.5 with sodium hydroxide solution. The immersion time was 30 s. The parts were then

rinsed with water and dried in air flow. On the parts a greenish, strongly iridescent layer had formed which later on turned out to be comprised of zinc/chromium oxide. In the corrosion test in the salt spray cabinet according to DIN 50021 SS it was surprisingly found that the chromate layer formed presented a spectacular corrosion protection until the appearance of first corrosion products of 1000 h according to DIN 50961 Chapter 10, in particular Chapter 10.2.1.2.

The novel greenish chromate layer had a layer thickness of approx.

800 nm and was produced by a process not involving any chromium(VI) and could be proven to be chromium(VI)-free.


The production method according to Example 1 for the novel, greenish chromium(VI)-free chromation is not very economical for conventional plants due to the relatively high temperature of the process solution. Further theoretical reflections concerning chromium(VI)-free chromate coating and further trials finally resulted in economical production conditions.

## **Theoretical Reflections Concerning Chromium(VI)-Free Chromation**

Chromate coating of zinc takes place by the formation of a so-called conversion layer on the zinc surface, i.e. the zinc surface chemically reacts with the chromate coating solution and is converted into a chromate layer. The formation of conversion layers is a dynamic process beyond chemical equilibrium. In order to describe the underlying processes, one must therefore employ chemical kinetics. By the especially established kinetic model it was possible to obtain starting points in order to optimise the present invention.


Conversion layer formation in a chromium(III)-based chromate coating solution may be described by means of two reaction equations:

I Elementary zinc passes into solution due to acid attack:



II and precipitates on the zinc surface as zinc chromium oxide together with chromium(III):

5



The kinetic model must encompass differential equations for the concentration developments of  $\text{Zn}^{2+}$ ,  $\text{H}^+$ ,  $\text{Cr}(\text{III})$  and for the thickness growth of the  $\text{ZnCrO}$  layer. In the reaction rate starting points it was taken into consideration by inserting the term  $1/(1 + P_1 \cdot m_{\text{ZnCrO}})^2$  that Reaction I is increasingly slowed down by the growing passive layer.  $P_1$  is a measure for tightness of the layer.

15

$$\begin{aligned} \frac{dc_{\text{Zn}^{2+}}}{dt} &= k_1 \times c_{\text{H}^+} / (1 + P_1 \times m_{\text{ZnCrO}})^2 && \text{Reaction I} \\ &- k_2 \times c_{\text{Zn}^{2+}} \times c_{\text{Cr}(\text{III})} + k_3 \times c_{\text{H}^+} \times \tanh(P_2 \times m_{\text{ZnCrO}}) && \text{Reaction II} \\ &+ k_T \times (c_{0,\text{Zn}^{2+}} - c_{\text{Zn}^{2+}}) && \text{Mass transfer} \end{aligned}$$

$$\begin{aligned} \frac{dc_{\text{H}^+}}{dt} &= -2k_1 \times c_{\text{H}^+} / (1 + P_1 \times m_{\text{ZnCrO}})^2 && \text{Reaction I} \\ &+ 2yk_2 \times c_{\text{Zn}^{2+}} \times c_{\text{Cr}(\text{III})} - 2yk_3 \times c_{\text{H}^+} \times \tanh(P_2 \times m_{\text{ZnCrO}}) && \text{Reaction II} \\ &+ k_T \times (c_{0,\text{H}^+} - c_{\text{H}^+}) && \text{Mass transfer} \end{aligned}$$

$$\begin{aligned} \frac{dc_{\text{Cr}(\text{III})}}{dt} &= -xk_2 \times c_{\text{Zn}^{2+}} \times c_{\text{Cr}(\text{III})} + xk_3 \times c_{\text{H}^+} \times \tanh(P_2 \times m_{\text{ZnCrO}}) && \text{Reaction II} \\ &+ k_T \times (c_{0,\text{Cr}(\text{III})} - c_{\text{Cr}(\text{III})}) && \text{Mass transfer} \end{aligned}$$

$$\frac{dm_{\text{ZnCrO}}}{dt} = k_2 \times c_{\text{Zn}^{2+}} \times c_{\text{Cr}(\text{III})} - k_3 \times c_{\text{H}^+} \times \tanh(P_2 \times m_{\text{ZnCrO}}) \quad \text{Reaction II}$$

The term  $\tanh(p_2 \cdot m_{\text{ZnCrO}})$  represents the indispensable precondition of reverse reaction II, namely the presence of ZnCrO. The tanh function provides for a smooth transition from 0 to 1, which may be adjusted with P2. The differential equation system was resolved numerically by means of a computer. As a result, the layer thickness developments and the concentration developments over time were obtained. As starting values for time  $t_0 = 0$  there were employed:

$$\begin{array}{lll} c_{\text{O,Zn}^{2+}} & = & 0 \\ c_{\text{O,H}^+} & = & 10^{-2} \text{ mol/l (pH 2)} \\ c_{\text{O,Cr(III)}} & = & 0,5 \text{ mol/l} \\ m_{\text{O,ZnCrO}} & = & 0 \end{array}$$

In Fig. [1] 38 the layer thickness developments for various values of the rate constant  $k_j$  are represented. For good corrosion protection, the passive layer should have maximum possible thickness and at the same time compactness.

Fig. 38 [(originally Illustration 1)] shows a computer simulation of the kinetic model for chromate coating of zinc for various rate constants.

The faster the initial dissolution of zinc (rate constant  $k_1$ ) is and the faster the dissolved zinc precipitates with the chromium(III) (rate constant  $k_2$ ), the thicker the chromate layer will become. Layer growth is strongly favored by the presence of zinc already dissolved in the bath, which fact resulted from simulations with  $c_{\text{O,Zn}^{2+}} > 0$ . A lower pH value favors dissolution of zinc but also brings about increased redissolution of the layer.

Based on the model, basically two demands may be established for producing a maximum possible thickness chromate layer. Reaction I and forward reaction II must take place as rapidly as possible, the reverse reaction II must remain slow. In this sense, there result the following

starting points:

**Reaction I**

- a     pH optimisation
- 5
- b     Avoiding carrying over of inhibitors from the zinc bath
- c     Addition of oxidants for accelerating zinc dissolution
- 10 d     Acceleration of zinc dissolution by formation of galvanic elements

**Forward reaction II**

- e     The rate constant  $k_2$  should be as high as possible. Chromium(III) complexes generally have slow kinetics. By using suitable ligands it
- 15     should be possible to accelerate the reaction rate.
- f     Upon use of further transition metal cations in the chromate coating solution there also result i.a. higher rate constants than for Cr(III). Moreover these transition metal cations may act as catalysts in ligand replacement on chromium(III).

20

**Reverse reaction II**

- g     Insertion of poorly redissolvable hydroxides, e.g. nickel, cobalt and/or copper hydroxide.

25

Serial investigations were carried out. Starting points a and b are known to the skilled person. Acceleration of zinc dissolution via points c and d did also result in thick coatings, however yellowish ones having a chromium/zinc ratio of 1:4 to 1:3, which only afforded low corrosion

30 protection. It was found that good corrosion protection values may only be obtained at chromium/zinc ratios above 1:2.

A higher chromium/zinc ratio at concurrently thicker chromate layers is obtained when the rate constant  $k_2$  (starting point e) is raised, or the

forward reaction II is accelerated. After the inventors of the present application had realised that hot chromium(III) solutions result in surprising passive layers, there are the following possibilities in connection with the inventors' theoretical reflections:

5

- Raising the temperature of the chromate coating solution and/or of the partial surface

- Raising the chromium(III) concentration in the process solution

10

- Acceleration of ligand replacement kinetics at the chromium(III).

Herefor one should know that chromium(III) in aqueous solutions is essentially present in the form of hexagonal complexes generally having high kinetic stability, and moreover that ligand replacement is the step determining the rate in forward reaction II. By the selection of suitable complex ligands, with which the chromium(III) forms kinetically less stable complexes,  $k_2$  is accordingly increased.

20

- Addition of elements having a catalytic effect on ligand replacement into the chromate coating solution.

In serial investigations chelate ligands (such as di- and tricarboxylic acids as well as hydroxydi- and hydroxytricarboxylic acids) as such forming kinetically less stable complexes with chromium(III), whereas the fluoride complexes are kinetically very stable. When using only such chelate ligands for complexing the chromium(III) and omitting fluoride in the passivation solution, excellent results were obtained even at a treatment temperature of only 60°C, as is shown by Examples 2 and 3.

30

## Example 2

Electrolytically bright-zinc coated (15 m) steel parts were immersed in an aqueous chromate coating solution containing:

- 5                    50 g/l  $\text{CrCl}_3 \cdot 6 \text{H}_2\text{O}$     (trivalent chromium salt)  
                     100 g/l  $\text{NaNO}_3$   
                     31,2 g/l malonic acid

the pH of which had previously been adjusted to 2.0 with sodium hydroxide solution. The immersion time was 60 s. Following rinsing and  
10 drying there resulted in the salt spray cabinet according to DIN 50021 SS a corrosion protection of 250 h until first attack according to DIN 50961.

Malonic acid is a ligand enabling more rapid ligand replacement kinetics at the chromium(III) than the fluoride of Example 1. Good corrosion  
15 protection by far exceeding the minimum requirement of DIN 50961 for Method Group C (yellow chromation) may thus already be achieved at 60°C.

### Example 3

20 Electrolytically bright-zinc coated (15 m) steel parts were immersed in an aqueous chromate coating solution consisting of:

- 50 g/l  $\text{CrCl}_3 \cdot 6 \text{H}_2\text{O}$     (trivalent chromium salt)  
                     3 g/l  $\text{Co}(\text{NO}_3)_2$   
                     100 g/l  $\text{NaNO}_3$   
25                    31,2 g/l malonic acid

previously adjusted to pH 2.0 with sodium hydroxide solution. Immersion time was 60 s. Following rinsing and drying there resulted in the salt spray cabinet according to DIN 50021 SS a corrosion protection of 350 h until first attack according to DIN 50961.

30

Cobalt is an element which was capable, in accordance with the model concept, of catalysing ligand replacement and moreover reducing reverse reaction II owing to insertion of kinetically stable oxides into the chromate layer, so that the chromate layer altogether should become



thicker. In this point, as well, the model concept established for the present invention is verified under practical conditions. Corrosion protection could once more clearly be enhanced in comparison with Example 3 by nothing but the addition of cobalt into the chromate

5 coating solution.

Novel greenish chromate layers on zinc were produced in analogy with Example 2 at 40, 60, 80 and 100°C. The layer thicknesses of the respective chromate layers were determined by RBS (=

10 Rutherford-Backscattering) testing. In the Table the corresponding corrosion protection values in hours of salt spray cabinet according to DIN 50021 SS until first attack according to DIN 50961 Chapter 10 are additionally listed.

15	<b>J / °C</b>	<b>thickness / nm</b>	<b>Corr. Prot. / h</b>
	40	100	50-60
	60	260	220-270
	80	400	350 450
	100	800	800-1200

20

Depending on the complex ligands used, which is malonate in Examples 2 and 3, it is partly possible to achieve even considerably higher layer thicknesses and corrosion protection values. By complex ligands containing as the complexing functional group nitrogen, phosphorus or

25 sulfur, (-NR<sub>2</sub>, -PR<sub>2</sub> wherein R independently is an organic, in particular aliphatic radical and/or H, and/or -SR, wherein R is an organic, in particular aliphatic radical or H,), it is possible to even produce the indicated layer properties within limits at room temperatures.

30

#### Example 4

Steel parts electrolytically coated with a zinc/iron alloy (0.4-0.6% iron) were immersed at 60°C in the following aqueous chromate coating solution:

35

50g/l  $\text{CrCl}_3 \cdot 6 \text{H}_2\text{O}$   
100g/l  $\text{NaNO}_3$   
31.2 g/l malonic acid

5 The solution was beforehand adjusted to pH 2.0 with NaOH. Immersion time was 60s. Following rinsing and drying a transparent, greenish, slightly grey, strongly iridescent layer was visible on the zinc/iron. In the salt spray cabinet in accordance with the above specified DIN and ASTM standards there resulted a corrosion protection of 360 h until first attack  
10 according to DIN 50961.

### Example 5

Steel parts electrolytically coated with a zinc/nickel alloy (8-13% nickel)  
15 were immersed at 60°C into the following aqueous chromate coating solution:

50g/l  $\text{CrCl}_3 \cdot 6 \text{H}_2\text{O}$   
100g/l  $\text{NaNO}_3$   
20 31.2 g/l malonic acid

The solution was beforehand adjusted to pH 2.0 with NaOH. Immersion time was 60s. Following rinsing and drying a transparent, greenish, dark-grey, strongly iridescent layer was visible on the zinc/nickel. In the salt  
25 spray cabinet in accordance with the above specified DIN and ASTM standards there resulted a corrosion protection of 504 h until first attack according to DIN 50961.

[Further advantageous ligands result from the enumeration according to  
30 claims 9 and 11.]

The novel greenish chromium(VI)-free chromate layer accordingly depending on the production temperature has a thickness of between 100 and 1000 nm, has a weakly green inherent color and a red-green iridescent

coloring. The chromate coating solution consists of trivalent chromates, moreover of conducting salts and mineral acids. Application of the chromate coating solutions is generally performed at temperatures above 40°C. The corrosion protection of unmarred greenish chromium(VI)-free chromate coatings depending on the production temperature amounts to 100-1200 h in the salt spray cabinet according to DIN 50021 SS until the first appearance of corrosion products. Thus the novel chromation satisfies the minimum requirements to corrosion protection for Method Groups C and D according to DIN 50961 (Chapter 10, Table 3), i.e. without chromium(VI) either in production or in the product.

By the present invention it is for the first time made possible to provide chromium(VI)-free conversion layers or passive layers on the basis of chromium(III), which do, however, furnish the corrosion protection of yellow chromations customary in the prior art - i.e., of chromium(VI)-containing passive layers.

This is a singular novelty in the entire galvanisation industry.

20

Hitherto on a chromium(III) basis only clear to blue layers, referred to as "blue passivation" in technical circles, were known which are variously applied practically.

25

Moreover yellowish-transparent layers with an addition of cerium are known which are, however, not used practically owing to the very costly cerium addition and their poor corrosion protection properties.

30 Moreover powdery-greenish layers are known for which the applicant - one of the leading enterprises in the field of surface technology - is not aware of any practical applications.

Even the difference in terms of color of the conversion layers of the present invention is conspicuous in Fig. 1, wherein three treatment methods were performed on zinc-plated screws.

- 5    The left-hand pile of screws in accordance with the illustration of Fig. 1 was subjected to a classical blue chromation [- as set forth on page 2 of the description under No. 1] in accordance with the standard of Method Group B according to DIN 50961 Chapter 10 table 3.
- 10   The right-hand pile of screws on the photograph according to Fig. 1 was subjected to a conventional yellow chromation in accordance with [page 2, No 2 of the present description] the standard of Method Group C according to DIN 50961 Chapter 10 table 3.
- 15   The center pile of screws shows the result of passivation of the screws by means of the method in accordance with the invention.

This is consequently a greenish-iridescent, transparent conversion layer, or passive layer.

20

Moreover the colors represented in Fig. 1 are the true colors, which can be seen from the fact that a color plate and moreover a grey wedge was jointly photographed for the purpose of neutral color representation.

- 25   As can be seen from the white test field "White" and from the corresponding field having the density ".00" from the grey wedge, both test fields are pure white, making evident the neutral filtering and the resulting realistic color representation.
- 30   In Fig. 2 scanning electron microscope (SEM) images of the conversion layers of a yellow chromation and of a blue chromation in accordance with the prior art are shown in comparison with the "chromitation" of the present invention.

The layer samples are derived from the correspondingly passivated zinc-plated iron screws shown in Fig. 2, lower half.

The samples treated in accordance with the invention (by "chromitation")  
5 presented a chromium(VI)-free conversion layer having a thickness of approx. 300 nm. In the photographs of Fig. 2 it should be considered that the layers were photographed in a viewing angle of approx. 40°, resulting in foreshortening by approx.  $\cos(40^\circ) = 0.77$ .

10 Based on the SEM images of the chromitation layer of the invention it therefore results that conversion layer thicknesses like in yellow chromation are obtained, however with the difference that the conversion layer of the invention does not contain any toxic chromium(VI).

15

The color photograph of Fig. 3 moreover shows the bandwidth of the iridescent coloring of the passive layer according to the invention under practical conditions.

20 It can already be seen in the photographs of Figs. 1 and 3 that the passive layer according to the invention does not contain any chromium(VI) ions as it lacks the typically yellow color (cf. right-hand pile of screws of the color photograph of [Enclosure] Fig. 1).

25 Objects according to the photograph of Figs. 1 and 3 as well as zinc-plated steel sheets passivated by the method of the invention were tested in the salt spray cabinet according to DIN50021SS or ASTM B 117-73, respectively, until the occurrence of first corrosion products according to DIN50961 Chapter 10. Herein it was surprisingly found that  
30 the passive layers of the present invention, and thus the objects passivated by the present method, fulfilled the corrosion protection of chromium(VI) passivations, i.e. yellow chromations, although not containing any chromium(VI).

It is worth mentioning that a typical yellow chromation of the prior art affords resistance for approx. 100 hours of exposure to saltwater in accordance with the above specified DIN or ASTN standard, whereas even the tenfold corrosion protection was achieved by the passive layers  
5 of the present invention.

The layers of the present invention as well as the methods for producing this layer, or the method for passivation of metal surfaces, thus satisfy the long-standing demand in this technical field for conversion layers  
10 doing without any toxic and carcinogenic chromium(VI) compounds while nevertheless even presenting and generally even excelling the corrosion protection of yellow chromations.

EP 00 34 040 A1 does describe a multitude of layers, wherein the colorations of the larger group thereof (produced under the standard  
15 conditions set forth by Barnes/Ward) are not specified, however which are referred to as clear. Two examples, i.e. Nos. 16 and 17, describe a greenish, borate-containing layer referred to as cloudy-dull to non-transparent.

20

Example 14 describes a layer affording a corrosion protection of no more than 4 hours.

In Example 15 of EP 00 34 040, an aluminum-containing layer is  
25 described which attains a corrosion protection of 100 hours. This is achieved - in comparison with the remaining examples - merely by the corrosion protection additive aluminum which is lacking in the present invention. Aluminum-free layers of identical or similar baths do, however, only present poor corrosion protection. The layer according to the  
30 invention offers significantly higher corrosion protection, namely up to 1000 h, even without this addition.

Examples 16 and 17 describe layers affording a corrosion protection of 300 and 200 hours in the salt spray test and thus in the range claimed

by the applicant. Description page 19, line 7 sets forth that layers of more than 1000 nm are required for good corrosion protection. It is thus understandable that these layers, without exception moreover produced from solutions containing boric acid, are described to be cloudy and  
5 rather non-transparent (page 14, line 10). The enhanced corrosion protection, in accordance with page 15, lines 1-5, is due to the insertion of borate-containing species.

The layer according to the invention, on the other hand, also offers high  
10 (and even higher) corrosion protection without this addition.

There is, however, another difference that is relevant in terms of patent law as well as in practical application: namely, the layers described in Examples 16 and 17 of EP 00 34 040 are soft and come off when wiped  
15 and consequently require some sort of hardening process as an aftertreatment (page 17, lines 12-21).

The present layers according to the invention are hard and resistant to wiping even **without a hardening process, and adhere well**. Corrosion  
20 protection layers which come off when wiped and which do not adhere to the substrate are useless for practical application.

In Fig. 4, a photograph is shown as a comparison example. This photograph represents the result of comparison tests carried out by the  
25 applicant in comparison with EP 00 34 040. In particular the applicant reproduced the Examples 16 and 17 given in this prior art. Herein steel sheets were immersed into the solutions described in Examples 16 and 17 of EP 00 34 040 and the respective treatment times were observed. Fig. 4 shows the layers on the substrate surfaces obtained in accordance  
30 with the prior art, namely from the top to the bottom the first and second sheets successively treated by immersion.

The photograph of Fig. 4 shows from the left to the right in the top half of the illustration a cloth whereby the layer produced in accordance with

Example 16 - prior art - was wiped, a zinc-plated steel sheet treated in accordance with Example 16, beside it a zinc-plated steel sheet treated in accordance with Example 17 - prior art - and on the extreme right also a cloth whereby the layer of Example 17 was wiped. In the second line  
5 on the left side - - beside the indication of Example 16 and beside it to the right ( beside the indication of Example 17) a respective zinc-plated steel sheet coated in accordance with the prior art is shown.

What is visible is a milky, white-greenish powdery coating which already  
10 comes off when wiped with a soft cloth even without application of particular pressure (see Fig. 4, top half of illustration). The prior art itself suggests that this layer is not a compact oxide zinc-/chromium conversion layer firmly adhering to the substrate sheet but a loosely overlying coating substantially consisting of chromium hydroxide. The pH  
15 for this coating must be so high that the precipitation limit for chromium hydroxides is already exceeded (page 26, line 12 of EP 0034 040). Precipitation of chromium hydroxide is kinetically inhibited and is favored by immersion of a more or less rough surface. The fact that the layer formation mechanism has to be a different one from the other examples  
20 may also be seen from the circumstance that with (Example 16 prior art) or without (Example 17) complexing agents more or less the same result was achieved. In practical reproduction of Examples 16 and 17 of the prior art it was moreover found that the layer became thicker, softer and more powdery with an increasing number of  
25 metal sheets coated in the solution. In addition, more and more chromium hydroxide precipitated, whereby the useful life of such a coating solution is limited to a few hours. The layer according to the invention, on the other hand, is produced only from suitable "rapid" complexes and furthermore in a distinctly acidic pH range. The solution is  
30 stable over months, presumably even years.

The measurements underlying Figs. 5 to 36 were performed with a glow-discharge spectrometer.



The element F and die anions could not be analysed by this method. O, H, Cl and K could not be quantified.

The following Table shows the concentration ranges for which calibration  
5 is valid:

Element	Concentration min. in	Concentration max. in
C	0.0067	3.48
S	0.0055	0.168
Cr	0.0001	99.99
Ni	0.0001	99.99
Co	0.0001	7.00
Zn	0.0001	99.99
Na	0.0001	0.0068
N	0.0001	6.90
B	0.0001	0.040
Fe	0.0005	99.91

20

Sample allocation in Figs. 5 to 36 results from the following Table:

Sample No.	Coating	Conditions	Measurement point
1	Chromititation on Zn (invention)	60°C, 1min, pH 2	A
			B
2		60°C, 2min, pH 2	A
			B
3		60°C, 1min, pH 2.5	A
4		60°C, 1.5min, pH 2.5	A
5		60°C, 2min, pH 2.5	A
6		100°C, 1min, pH 2	A
			B
			C
			D
7	Chromititation on Zn/Fe	60°C, 1min, pH 2	A
			B

35

8	Blue chromation on Zn	20°C, 30s, pH 1.8	A
9	Yellow chromation on Zn	20°C, 45s, pH 1.8	A
			B

- 5 Fig. 37 shows a Table containing the evaluations of the depth profile measurements, which indicates that all of the (chromitation) layers of the invention have thicknesses exceeding 100 nm.

## Abstract

### Chromium(VI)-Free Conversion Layer and Method for Producing It

5

A chromium(VI)-free, chromium(III)-containing and substantially coherent conversion layer on zinc or zinc alloys presenting, even in the absence of further components such as silicate, cerium, aluminum and borate, a corrosion protection of approx. 100 to 1000 h in the salt spray  
10 test according to DIN 50021 SS or ASTM B 117-73 until first attack according to DIN 50961 Chapter 10; being clear, transparent and substantially colorless and presenting multi-colored iridescence; having a layer thickness of approx. 100 nm to 1000 nm; and being hard, adhering well and being resistant to wiping.

15

[(Fig. 2)]